



Last Update: 07/09/2015

PA100EEV Technical Data Sheet

Test	Standard	Result	Measured Unit
Density	ISO 845	100	Kg/m ³
Tensile strength	ISO 1798	1461	kPa
Elongation	ISO 1798	154	%
Compression 10%	ISO 844	131	kPa
Compression 25%	ISO 844	133	kPa
Compression 50%	ISO 844	232	kPa
Working Temperature Range	Internal	-60 / 80	°C
Water Absorption %Vol (max)	Internal	1	%
Shore A	ISO 868	25	A

Palfoam is a closed cell cross-linked polyethylene foam block.

Tolerances other than the above may be negotiated.

Dimensional stability 24 hr at 70C < 2%.

If holes were created during the foaming process, no more than 6 holes of diameter 2mm per 1m² sheet are acceptable.

This information on Palfoam chemically cross-linked polyethylene foam is presented to the best of our knowledge.

Data represents typical values measured on a 10 mm thick specimen and should be considered as a guideline only.

PALZIV Kibbutz Ein Hanatziv 10805 Israel. Tel: 972-4-6062999 Fax: 972-4-6062958

www.palziv.com Email: contact@palziv.com