



Palziv Ein Hanatziv M.P. Emek Beit Shean 10805 Israel
Tel: +972 46 06 29 99 Fax: +972 46 06 29 58

www.palziv.com
contact@palziv.com



Company Number: 570040535

Consol. Busn Number: 557634052

Product Specification - PB65

Last update: 06/24/10

Desc.	Standard	Value	Unit
Density	ISO 845	65	Kg/m ³
Tensile strength	ISO 1798	1034	kPa
Elongation	ISO 1798	104	%
Compression 10%	ISO 844	107	kPa
Compression 25%	ISO 844	132	kPa
Compression 50%	ISO 844	214	kPa
Compression Set-0.5 Hrs	ISO 1856	6.0	%
Compression Set-24 Hrs	ISO 1856	2.0	%
Compression Set 50% 0.5 Hrs	ISO 1856	15.0	%
Compression Set 50% 24 Hrs	ISO 1856	7.0	%
Working Temperature Range	Internal	-60 \ 80	°C
Water Absorption %Vol (max)	Internal	1	%
Thermal Conductivity at 10C	ASTM C177	0.0500	W/mK
Thermal Conductivity at 40C	ASTM C177	0.0550	W/mK
Shore-A	ASTM D2240	23	A
Shore-OO	ASTM D2240	70	oo

Palfoam is a closed cell cross-linked polyethylene foam block.

Tolerances other than the above may be negotiated.

Dimensional stability 24 hr at 70C < 2%.

If holes were created during the foaming process, no more than 6 holes of diameter 2mm per 1m² sheet are acceptable.

This information on Palfoam chemically cross-linked polyethylene foam is presented to the best of our knowledge. Data represents typical values measured on a 10 mm thick specimen and should be considered as guidelines only.

PALZIV Kibbutz Ein Hanatziv 10805 Israel. Tel: 972-4-6062999 Fax: 972-4-6062958

www.palziv.com Email: contact@palziv.com